

Data Sheet **1075 Abrasion Resistant Super Para Rubber**

| | |
|--------------------|----------|
| Data Sheet Type | Final |
| Material Reference | 1075 |
| Polymer | NR |
| Date Issued | 01/06/26 |



Description

A high quality Para Rubber material with extremely good mechanical properties and excellent abrasion resistance. This material is used across Europe in Ballistic Curtain applications, at both indoor and outdoor ranges, protecting target shooters from ricocheting bullets. The material is also recommended for a wide variety of wear applications both wet and dry.

| Specifications | Values | Test Methods |
|---|---------------------------------|-----------------|
| Abrasion Resistance | 65 mm ³ | 5N UNE-ISO 4649 |
| Elongation at Break | 600 % | ASTM D412 |
| Highest Recommended Working Temperature | 80 °C | None |
| Lowest Recommended Working Temperature | -30 °C | None |
| Shore Hardness (Shore A) | 38 ° Shore | ASTM D2240 |
| Specific Gravity | 0.97 g/cm ³ +/- 0.03 | ASTM D2240 |
| Tear Strength - Angle | 25 kg/cm | UNE ISO 34-1 |
| Tensile Strength | 25 MPA | ASTM D412 |

Purposes



Abrasive Resistance



Tear Resistant



Wear Resistant

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.